

ROADWARE

MenderBlender™

Dry Latex Resurfacing Product



FOR BLENDING CONCRETE MENDER REPAIRS WITH EXISTING CONCRETE

“Just add water!”

- **Easy to Apply - Indoors or Outdoors**
- **Apply over cured Roadware 10 Minute Concrete Mender™ repairs for color blending and enhancement. Use on sidewalks, driveways, and walls.**
- **Apply up to 1/16” thick**

Product Description

MenderBlender is a special blend of cements, aggregates and exclusive modifiers. Designed for general purpose and high performance concrete resurfacing applications.

Packaging and Yield

MenderBlender is available in 10 lb. units. A 10 lb. unit will yield up to 75 square feet when brush or broom applied.

Technical Data

Compressive strength 28 day Exceeds 4000 psi ASTM C109
Compressive strength 7 day Exceeds 3000 psi ASTM C109
Compressive strength 1 day Exceeds 1500 psi ASTM C109
Flexural Strength 28 day Over 800 psi ASTM C 78
Freeze / Thaw Durability Excellent ASTM C 666
Bond Strength Exceeds 150 psi ACI 503 R
Color Light Concrete Gray

This product will have a general “new” concrete appearance when cured that will change over time just like concrete. Because no two slabs of concrete are alike and the existing concrete color can not be matched exactly in all cases, No warranty or guarantee is made on the basis of appearance or color. ALWAYS TEST ON A NON-CONSPICUOUS AREA OF THE SLAB BEFORE USE.

Item 2001
Roadware MenderBlender
10 lbs resealable can
4 cans per case



Read Carefully Before Use:

FOR BEST RESULTS / LIMITATIONS

APPLY TO CLEAN SUBSTRATES, REMOVE DUST, PAINT CURING COMPOUNDS AND ANY FOREIGN MATTER PRIOR TO USE. REPAIRS MADE WITH ROADWARE 10 MINUTE CONCRETE MENDER SHOULD BE GROUND FLAT WITH A ROUGH FINISH.

Do not apply below 40 degrees Fahrenheit. Apply material within 1 hour of mixing. Do not retemper already mixed product. Store in a cool, dry place.

MIX WITH WATER ONLY. Approximately 2 quarts of water is required to mix 10 lb. (one can) of product. Always add and mix product into liquid. Apply mixed product within 1 hour. Small amounts of product will set faster. Hold back 1 part of water and adjust final part water for consistency desired. Apply material above 40°F. Rub or scratch mixed material onto surface just prior to application with a trowel edge - then immediately smooth over with the same trowel. Scratching the first coat insures a good bond. Finish and blend into concrete with a brush or broom. Overband cracks a few inches or treat the entire section.

Not recommended for use on hard trowelled surfaces or areas with heavy forklift traffic.

Allow to cure until fully set. Restrict to light traffic only for 24 hours. Rain within the first 72 hours may cause temporary discoloration. Original color will be restored within a few weeks.



ROADWARE INCORPORATED
381 BRIDGEPOINT DRIVE
SOUTH SAINT PAUL, MN 55075

800-522-7623

TEL: 651-457-6122

FAX: 651-457-1420

sales@concretemender.com

www.roadwareinc.com